

Test Report 3M 467MP vs HB2065

Test Item:	Test Report		Test Method
Cat No.:	3M 467MP	HB2065 Production no.:71202215	
Printed Krafted Paper	0.110mm*100g/m ²	100g/m ²	
Coating thickness (mm)	0.060	0.060 ~ 0.065	-
Adhesion (g/25mm)	1466 ~ 1605	1593 ~ 1852	PSTC-1
Holding Power (1kg/25mm*25mm)	> 48 hrs	> 48 hrs	PSTC-7
Holding Power at 195°C (1kg/25mm*25mm)	2 min ↓	> 24 hrs	PSTC-7
Holding Power at 195°C (0.5kg/25mm*25mm)	> 24 hrs	> 24 hrs	PSTC-7
Holding Power at 100°C (1kg/25mm*25mm)	> 24 hrs	> 24 hrs	PSTC-7
Holding Power at -30°C (1kg/25mm*25mm)	> 24 hrs	> 24 hrs	PSTC-7
Initial Tack (cm)	25 ~ 28	A:18.5 B:3	PSTC-6 (#14 Ball)
Remarks	1.Date: Feb. 12, 2008 2.Test condition: 23 ± 5°C ; 55 ± 10% RH 3.Storage condition: 20 ~ 30 °C and avoid exposing to high humidity		